

TECHNICAL DATA

Teonex[®]

Q65FA

■ Characteristics

Super clear type for optical uses. Excellent heat stability

■ Typical Applications

OLED, electric paper, PV-cell

■ Pretreatment

one side

■ Technical Data

Item		Unit	Q65FA Type	Test method
Thickness		μm	200	JIS C2151
Tensile strength	MD	MPa	250	JIS C2318
	TD		250	
Tensile elongation	MD	%	110	JIS C2318
	TD		110	
Thermal Shrinkage (150 deg C × 30 mins.)	MD	%	0.0	JIS C2318
	TD		0.0	
Thermal Shrinkage (200 deg C × 10 mins.)	MD	%	0.1	JIS C2318
	TD		0.0	
Surface roughness Ra	Smooth side	nm	0.8	JIS B0601
	Rough side		10.0	
Total light transmittance		%	87.0	JIS C7361
Haze		%	0.8	JIS C7361

1.The information contained herein is believed to be reliable and correct.

2.Please refer to the MSDS for product safety data.

3.Information is presented without guarantee or warranty.

Teijin DuPont Films Japan Limited All Rights Reserved.

R&D Planning Section Development Center
TEL.+81-584-64-7176 FAX.+81-584-64-7189